

## ABSTRACT

This invention is related to an adhesive composition which may be used to bond or seal tissue in vivo. The adhesive composition is readily formed from a two component mixture which includes a first part of a protein, preferably a serum albumin protein, in an aqueous buffer having a pH in the range of about 8.0–11.0 and a second part of a water-compatible or water-soluble bifunctional crosslinking agent. When the two parts of the mixture are combined, the mixture is initially a liquid which cures in vivo on the surface of tissue in less than about one minute to give a strong, flexible, pliant substantive composition which bonds to the tissue and is absorbed in about four to sixty days. The adhesive composition may be used either to bond tissue, to seal tissue or to prevent tissue adhesions caused by surgery.

EA-



# US005583114A

## United States Patent [19]

Barrows et al.

[11] Patent Number:

5,583,114

Date of Patent:

Dec. 10, 1996

## [54] ADHESIVE SEALANT COMPOSITION

[75] Inventors: Thomas H. Barrows, Cottage Grove; Terry W. Lewis, Woodbury; Myhanh

T. Truong, Blaine, all of Minn.

[73] Assignee: Minnesota Mining and

Manufacturing Company, Saint Paul,

[21] Appl. No.: 281,473

[22] Filed: Jul. 27, 1994

[51] Int. Cl.<sup>6</sup> ...... A61K 38/00; A61K 39/00; C07K 1/00

... 514/21; 514/2; 514/4; 530/362; 530/363; 530/366; 530/830; 424/77; 424/78.02; 424/78.06; 424/179.1; 424/193.1; 424/194.1; 424/422; 424/423; 424/428;

525/54.1 [58] Field of Search ...... 514/21, 2, 4; 530/350, 530/362, 363, 366, 830; 424/77, 78.02, 78.06, 422, 423, 428; 524/54.1

#### [56] References Cited

## U.S. PATENT DOCUMENTS

	2.688.610	9/1954	Elins et al 260/117
	4.101.380		260/117
		7/1978	Rubinstein et al 530/350
	4.163.097	7/1979	Baumann et al 525/531
	4,356,319	11/1982	Pouczek
	4.416.314		128/156
		11/1983	Battista 260/117
	4.670.417	6/1987	Iwasaki et al
	4,692,462	9/1987	Banerjee
	4.839.345	6/1989	Doi et al
	, ,		Doi et al
	4,851,513	7/1989	Devore et al
	<i>5</i> ,162,430	11/1992	Rhee et al
	5.385.606	1/1995	Kowanko
	-,,	/ / 3	106/124
FORFICNI RATES TO DO CO.			

### FOREIGN PATENT DOCUMENTS

0194807A3 9/1988 European Pat. Off. .

2551660 3/1985 France.

WO90/13540 11/1990 WIPO.

WO92/02238 2/1992 WIPO. WO94/03155 2/1994 WIPO.

## OTHER PUBLICATIONS

Abuchowshi et al, The Journal of Biological Chemistry, vol. 252, No. 11, pp. 3578-3581, Jun. 10, 1977. D'Urso et al. Biotechnology Techniques, vol. 8, No. 2, pp. 71-76, Feb. 1994.

Two-Component Fibrin Sealant Tisseel® Kit Brochure.

Abstract, Abdella et al., "A New Cleavable Reagent : Cross-linking and Reversible Immobilization of Protein Biochem. Methods, 91:16228v, 1979.

Kalman et al., "Synthesis of a Gene for Human Sen-Albumin and Its Expression in Sacchromyces cerevisiae Nucleic Acids Research, vol. 18, No. 20, 1990, pp. 6075-6081.

Sleep et al., "The Secretion of Human Serum Albumin from the Yeast Saccharomyces cerevisiae Using Five Different Leader Sequences", Bio/Technology, vol. 8, Jan. 1990, pp.

Sijmons et al., "Production of Correctly Processed Human Serum Albumin in Transgenic Plants", Bio/Technology, vol. 8, Mar. 1990, pp. 217-221.

Quirk et al., "Production of Recombinant Human Scrum Albumin from Saccharomyces cerevisiae", Biotechnology and Applied Biochemistry, 11,273-287 (1989).

D'Urso et al., "New Hydrogel Based on Polyethylene Glycol Cross-Linked with Bovine Scrum Albumin", Biotechnology Techniques, vol. 8, No. 2 (Feb. 1994) pp. 71-76.

Primary Examiner-Elizabeth C. Weimar Assistant Examiner-Abdel A. Mohamed Attorney, Agent, or Firm-Gary L. Griswold; Walter N. Kim; Paul W. Busse

#### [57] ABSTRACT

This invention is related to an adhesive composition which may be used to bond or seal tissue in vivo. The adhesive composition is readily formed from a two component mixture which includes a first part of a protein, preferably a scrum albumin protein, in an aqueous buffer having a pH in the range of about 8.0-11.0 and a second part of a watercompatible or water-soluble bifunctional crosslinking agent. When the two parts of the mixture are combined, the mixture is initially a liquid which cures in vivo on the surface of tissue in less than about one minute to give a strong, flexible, pliant substantive composition which bonds to the tissue and is absorbed in about four to sixty days. The adhesive composition may be used either to bond tissue, to scal tissue or to prevent tissue adhesions caused by surgery.

17 Claims, 3 Drawing Sheets